

TECHNICAL DATA SHEET
KYNAR® 1000 HD

氟化聚合物颗粒

KYNAR®树脂是氟化热塑性同聚物。杰出特性：化学抗性，抗紫外线，高屏障性能，高纯度，良好的机械和热机械性能。KYNAR® 1000 HD树脂是用于压缩和转移成型的标准颗粒级别，用于挤出厚壁零件：块状、棒状、板材、管材。

TYPE

PVDF

MAIN APPLICATIONS

- 高纯度
- CPI - 分销
- 模塑
- 管道
- 通风管
- CPI - 预制件

交货形式

- 粒子

转化过程

- 注塑成型

RHEOLOGICAL PROPERTIES

特性	价值	UNIT	测试标准
熔融粘度, 230°C (445°F) 在100 s-1	15 - 20	kPo	ASTM D3835
收缩率, 正常 (t+24h)	2	%	ISO 294-4
收缩率, 并行 (t+24h)	2	%	ISO 294-4
熔融指数 (MFR), 235°C / 5 公斤 (455°F / 11 磅)	1 - 3	g/10分钟	ASTM D1238
熔融体积流动速率 (MVR), 230°C / 5 公斤 (446°F / 11 磅)	1.1	cm³/10分钟	ISO 1133

MECHANICAL PROPERTIES

特性	价值	UNIT	测试标准
屈服应力, 23°C (73°F)	44.8 - 55.2	MPa	ISO 527-1/-2
屈服应变, 23°C (73°F), 50 mm/min	9	%	ISO 527-1/-2
断裂应力, 23°C (73°F)	34.5 - 55.2	MPa	ASTM D638
断裂标称应变, 23°C (73°F), 50 mm/min	>50	%	ISO 527-1/-2
压缩强度, 23°C (73°F)	68.9 - 103	MPa	ASTM D695
简支梁缺口冲击强度, Z轴, 23°C (73°F)	No Break		ISO 179 1eU
简支梁无缺口冲击强度, -30°C (-22°F)	No Break		ISO 179 1eU
简支梁缺口冲击强度, 23°C (73°F)	22	千焦/平方米	ISO 179 1eA
简支梁缺口冲击强度, -30°C (-22°F)	5	千焦/平方米	ISO 179 1eA
邵D硬度	76 - 80		ASTM D2240
弯曲模量, 23°C (73°F)	1450 - 2310	MPa	ISO 178

KYNAR® 1000 HD

特性	价值	UNIT	测试标准
拉伸模量, 23°C (73°F), 1 mm/min	2000	MPa	ISO 527-1/-2

THERMAL PROPERTIES

特性	价值	UNIT	测试标准
玻璃转变温度, 10°C/分钟	-40	°C	ISO 11357-1/-2
维卡软化温度, 50N在50°C/h	138	°C	ISO 306
限氧指数 (LOI)	60	%	ASTM D2863
线性热膨胀系数, 23°C (73°F)	11.9 - 14.4	10E-6 / °K	ASTM D696
比热温度, 23°C (73°F)	745 - 958		ISO 11357-1/-2
热变形温度, 1.8 MPa	104	°C	ISO 75-1/-2
热变形温度, 1.8 MPa , 138°C/h	105 - 115	°C	ASTM D648
热变形温度, 0.45 MPa , 138°C/h	125-140	°C	ASTM D648
导热系数	0.17 - 0.19	W/m-K	ASTM D433
熔点, 10°C/分钟	172	°C	ISO 11357-1/-3

ELECTRICAL PROPERTIES

特性	价值	UNIT	测试标准
相对漏电起痕指数	600		IEC 60112
相对介电常数, 100赫兹	10.5		IEC 62631-2-1
相对介电常数, 1MHz	7		IEC 62631-2-1
相对热指数	150		
损耗因数, 100赫兹	270	E-4	IEC 62631-2-1
损耗因数, 1MHz	2400	E-4	IEC 62631-2-1

OTHER PROPERTIES

特性	价值	UNIT	测试标准
吸湿, 在23°C (73°F) / 50%相对湿度下的平衡状态	0.015	%	ISO 62
吸水, 23°C (73°F) 下饱和于水中	0.03	%	ISO 62
, 23°C (73°F)	1.77 - 1.79	克/厘米³	ISO 1183-1

包装

- Available packaging:
- 1000 kg / 2205 lb rigid container
 - 25 公斤 / 55 磅袋
 - 25 kg / 55 lb rigid container
 - 680 kg /1500 lb rigid container
 - 800 kg / 1765 lb big bag

特殊特性

- 火焰和烟雾

KYNAR® 1000 HD

阿科玛 (中国) 投资有限公司
北京市朝阳区
太阳宫中路12号楼9层904室
邮政编码 : 100028
+86 (10) 8415 8360

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

arkema.com

