

TECHNICAL DATA SHEET
KYNAR® 9000 HD

氟化聚合物颗粒

KYNAR®树脂是氟化热塑性同聚物。
杰出特性：化学抗性，抗紫外线，高隔离性能，高纯度，良好的机械和热机械性能。
KYNAR® 9000 HD树脂是用于注射成型薄壁零件和多丝挤出的标准颗粒级别。

TYPE	交货形式
PVDF	• 粒子
MAIN APPLICATIONS	转化过程
• 模塑	• 注塑成型

RHEOLOGICAL PROPERTIES

特性	价值	UNIT	测试标准
熔融粘度, 230°C (445°F) 在100 s-1	6-10	kPo	ASTM D3835
收缩率, 正常 (t+24h)	2	%	ISO 294-4
收缩率, 并行 (t+24h)	2	%	ISO 294-4
熔融指数 (MFR), 235°C / 5 公斤 (455°F / 11 磅)	16 - 30	g/10分钟	ASTM D1238
熔融体积流动速率 (MVR), 230°C / 5 公斤 (446°F / 11 磅)	10	cm³/10分钟	ISO 1133

MECHANICAL PROPERTIES

特性	价值	UNIT	测试标准
屈服应力, 23°C (73°F)	44.8 - 55.2	MPa	ASTM D638
断裂应力, 23°C (73°F)	34.5 - 55.2	MPa	ASTM D638
压缩强度, 23°C (73°F)	68.9 - 103	MPa	ASTM D695
简支梁缺口冲击强度, Z轴, 23°C (73°F)	232	千焦/平方米	ISO 179 1eU
简支梁无缺口冲击强度, -30°C (-22°F)	218	千焦/平方米	ISO 179 1eU
简支梁缺口冲击强度, 23°C (73°F)	11	千焦/平方米	ISO 179 1eA
简支梁缺口冲击强度, -30°C (-22°F)	5	千焦/平方米	ISO 179 1eA
悬臂梁无缺口冲击强度, 23°C (73°F)	1070-4270	J/m	ASTM D256
悬臂梁缺口冲击强度, 23°C (73°F)	96-214	J/m	ASTM D256
邵D硬度	76 - 80		ASTM D2240
断裂标称应变, 23°C (73°F), 50 mm/min	40	%	ISO 527-1/-2
屈服应变, 23°C (73°F), 50 mm/min	8	%	ISO 527-1/-2
弯曲模量, 23°C (73°F)	1380 - 2310	MPa	ASTM D790

KYNAR® 9000 HD

特性	价值	UNIT	测试标准
拉伸模量, 23°C (73°F)	2310	MPa	ASTM D638
相对钢材的动摩擦系数, 23°C (73°F)	0.14		ASTM D1895
相对钢材的静摩擦系数, 23°C (73°F)	0.2		ASTM D1894
耐磨性, CS 17转轮, 负载 1 公斤, 1000 次循环	5 - 9	毫克	ASTM G195-13A

THERMAL PROPERTIES

特性	价值	UNIT	测试标准
玻璃转变温度, 10°C/分钟	-40	°C	ISO 11357-1/-2
维卡软化温度, 50N在50°C/h	141	°C	ISO 306
限氧指数 (LOI)	60	%	ASTM D2863
线性热膨胀系数, 23°C (73°F)	119 - 144	10E-6 / °K	ASTM D696
热变形温度, 1.8 MPa	110	°C	ISO 75-1/-2
热变形温度, 1.8 MPa , 138°C/h	105 - 115	°C	ASTM D648
热变形温度, 0.45 MPa , 138°C/h	125-140	°C	ASTM D648
熔点, 10°C/分钟	171	°C	ISO 11357-1/-3

ELECTRICAL PROPERTIES

特性	价值	UNIT	测试标准
介电常数, 1kHz	0.5 - 4.5		ASTM D150
体积电阻率 (横向) , DC , 20°C (68°F) /50%RH	2.0E+12	欧姆*米	ASTM D257
相对介电常数, 100赫兹	10		IEC 62631-2-1
相对介电常数, 1MHz	7.5		IEC 62631-2-1
损耗因数, 100赫兹	310	E-4	IEC 62631-2-1
损耗因数, 1MHz	2160	E-4	IEC 62631-2-1
损耗因数	0.01 - 0.21		ASTM D150

OTHER PROPERTIES

特性	价值	UNIT	测试标准
吸湿, 在23°C (73°F) / 50%相对湿度下的平衡状态	0.015	%	ISO 62
吸水, 23°C (73°F) 下饱和于水中	0.03	%	ISO 62
, 23°C (73°F)	1.76 - 1.78	克/厘米³	ISO 1183-1

包装




- Available packaging:
- 1000 公斤大袋
 - 25 公斤 / 55 磅袋

特殊特性

- 火焰和烟雾

KYNAR® 9000 HD

DIAGRAMS



阿科玛 (中国) 投资有限公司
北京市朝阳区
太阳宫中路12号楼9层904室
邮政编码 : 100028
+86 (10) 8415 8360

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

