

TECHNICAL DATA SHEET  
RILSAN® PA11 ESY BLACK 7298

POLYAMIDE 11 POWDER

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® ESY range is designed for coating metal parts using the electrostatic spraying process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

DESIGNATION

PA11

MAIN APPLICATIONS

- Water Fluid Coating - Water Accessories
- Oil And Gas - Energy Pipe Coating
- Automotive/Truck - Automotive Coating

DELIVERY FORM

- Powder

TRANSFORMATION PROCESSES

- Electrostatic spraying

ADDITIVES

- Heat Stabilized

MECHANICAL PROPERTIES

特性	DRY / COND VALUE*	UNIT	测试标准
Hardness, Shore D, 23°C (73°F)	- / 72		ISO 868
Hardness, Persoz, 23°C (73°F)	- / 270		ISO 1522
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 17	mg	ISO 9352

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

THERMAL PROPERTIES

特性	价值	UNIT	测试标准
Melting temperature, 10°C/min	183-188	°C	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181	°C	ISO 306

# RILSAN® PA11 ESY BLACK 7298

## OTHER PROPERTIES

特性	价值	UNIT	测试标准
Covering efficiency (100 µm)	0.20	kg/m²	Internal Arkema
Water absorption, 24h	≤ 1	%	ISO 62
Median particles (D50)	30	µm	ISO 13320
Approximate RAL number	9005		
Salt spray test	Good adhesion after 2000 hours		ISO 9227
Specific gravity of coating, 20°C (68°F)	1.19	g/cm³	ISO 1183-1
Apparent density, Non compacted	0.44		ISO 1068
Apparent density, Compacted	0.62		ISO 1068
Particle Size Distribution (PSD) (Fine particles < 20 µm)	20	%	ISO 13320
Particle Size Distribution (PSD) (Coarse particles > 100 µm)	1	%	ISO 13320

## 包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 20 kg / 44 lb bags

## 保质期

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## SPECIAL CHARACTERISTICS

- Bio-based