

TECHNICAL DATA SHEET  
RILSAN® PA11 T BLACK 7450 AC

POLYAMIDE 11 POWDER

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® T range is designed for coating metal parts using the fluidized bed dip coating process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

TYPE

PA11

MAIN APPLICATIONS

- Water Fluid Coating - Water Accessories
- Powder Coating - Renewable Energy
- Powder Coating - Dish Washer Basket
- Automotive/Truck - Automotive Coating

DELIVERY FORM

- Powder

TRANSFORMATION PROCESSES

- Fluidized Bed Dipping

ADDITIVES

- Heat Stabilized

MECHANICAL PROPERTIES

特性	DRY / COND VALUE*	UNIT	测试标准
Hardness, Shore D, 23°C (73°F)	- / 70		ISO 868
Coating impact, 23°C (73°F)	- / ≥ 2	J	ASTM G14
Hardness, Persoz, 23°C (73°F)	- / 250		ISO 1522
, Wheel CS 17, load 1 kg, 1000 cycles	- / 13	mg	ISO 9352

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

THERMAL PROPERTIES

特性	价值	UNIT	测试标准
Melting temperature, 10°C/min	183-188	°C	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181	°C	ISO 306

# RILSAN® PA11 T BLACK 7450 AC

## OTHER PROPERTIES

特性	价值	UNIT	测试标准
Covering efficiency (300 µm)	0.33	kg/m²	Internal Arkema
Water absorption, 24h	≤ 1	%	ISO 62
Median particles (D50)	100-130	µm	ISO 13320
Approximate RAL number	9011		
Salt spray test	Good adhesion after 2000 hours		ISO 9227
Specific gravity of coating, 20°C (68°F)	1.05	g/cm³	ISO 1183-1
Apparent density, Non compacted	0.52		ISO 1068
Apparent density, Compacted	0.62		ISO 1068
Particle Size Distribution (PSD), Fine particles (≤ 40 µm)	4	%	ISO 13320
Particle Size Distribution (PSD), Coarse particles (> 254 µm)	5	%	ISO 13320

## 包装

Available packaging:

- 25 公斤 / 55 磅 袋

## 保质期

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## SPECIAL CHARACTERISTICS

- Bio-based

Headquarter: Arkema France  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

arkema.com

